CI/SfB		
	Yt3	
CAW Z20		
Uniclass L6739:P7112		

# illbruck making it perfect.

# **Description**

PU230 is a thixotropic polyurethane paste adhesive.

Applications include: fixing and bonding of windows, doors, staircases architrave's, boat building, fixing of carpet grippers to concrete and wooden floors, etc. The adhesive is highly

water-resistant and can be used in applications where regular wetting and/or high humidity is anticipated.

#### Colour

Translucent

#### **Packaging**

310 ml cartridges (12 per carton)

#### **Technical Information**

Characteristic	Result	
Composition	Thixotropic polyurethane paste	
Conformance	EN204: D4	
Specific Gravity	1.08	
Viscosity (at 20°C)	100,000 cps	
CureTime (at 20°C)	30 - 40 minutes	
OpenTime	6-7 minutes	
Application Temperature	+5°C to +40°C	
Service Temperature	-50°C to +120°C	
Storage	Store in dry shaded conditions between +5°C and+25°C.	
Shelf Life	9 months when stored as recommended in original unopened packaging.	

# **Necessary Tools**

 Standard cartridge skeleton gun and a sharp knife to cut nozzle.

#### **Protective Equipment**

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

#### **Preparation**

- Always carry out a test to confirm compatibility prior to
- All surfaces to be bonded must be close fitting, degreased, clean, and free from dust and any other contamination.
- Dampening the surfaces to be bonded with a moist cloth or spray can increase the rate of cure.
- Roughen non-porous surfaces.

# **Application**

- Cut off end of thread with a sharp knife, avoiding damage to the thread. Trim the nozzle to the required diameter.
- Ensure good contact between the joint surfaces before applying adhesive. Apply the adhesive to one or both surfaces and spread quickly using a notched spreader.
- Bring the two components together within 2 minutes and clamp securely together for at least 30 minutes until sufficient bond strength has developed. Sufficient working strength will normally develop after 30 minutes.



# **PU230**

# **Wood Adhesive**



# Usage / Purpose

PU230 is a thixotropic PU adhesive paste which cures rapidly to form an exceptionally strong water resistant bond. It is ideal for use in all types of joinery, and construction and repair applications where a strong permanent bond is required between porousporous and porous-nonporous surfaces.

# **Key Benefits**

- Waterproof adhesive suitable for external use- meets the requirements of EN 204 (D4)
- Forms an exceptionally high bond strength to most building materials, even damp substrates
- Rapid curing formulation bonds in as little as 5 minutes
- Gap filling action achieves a high strength bond with irregular or uneven substrates
- Rapid curing and outstanding bond strength without the need for priming or surface treatment

# PU230

# **Wood Adhesive**



#### Coverage

250 to 400 ml per m<sup>2</sup>, depending on substrate.

# **Cleaning**

Remove excess adhesive immediately with AA290 PU Foam Cleaner. Ensure surface is solvent resistant before cleaning. Cured adhesive can only be removed mechanically.

#### **Please Note**

Not suitable for bonding polyethylene, polypropylene, Teflon® or Nylon. Moisture content of wood must not exceed 30%w/w. Do not use on sheet laminate.

# **Health & Safety Precautions**

Safety data sheet must be read and understood before use.



#### Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

# **Guarantee / Warranty**

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



# tremco illbruck Limited

Coupland Road, Hindley Green WN2 4HT Wigan United Kingdom T: +44 1942 251400 F: +44 1942 251410

info.uk@tremco-illbruck.com www.tremco-illbruck.co.uk