

Cl/SfB	Yt4
CAW P22	
Uniclass L6751: P7112	

Description

FM310 is a rapid curing gun grade expanding polyurethane foam that is suitable for general gap filling, bonding and insulation applications.

Colour

Green

Packaging

750 ml pressurised canister (12 per carton)

Technical Information

Property	Test Method	Results
Composition		Polyurethane Foam
Fire Classification	DIN 4102-1	B3
Yield		46 litres
Water Absorption	EN 1609	0.2 kg/m ²
Density	LAB 015	15- 25 kg/m ³
Tack Free Time	FEICA TM 1014	10 minutes
Cutting Time	FEICA TM 1005	45 minutes
Loading Time		24 hours
Compressive Strength (10%)	FEICA TM 1011	34 kPa
Elongation at Break	FEICA TM 1018	21%
Thermal Conductivity	EN 12667	36 mW/m.K
Maximum Acoustic Rating	EN ISO 140-1 : 2005-03	62 dB
Service Temperature		Short Term: -40°C to +130°C Long Term: -40°C to +90°C
Application Temperature		Canister: +10°C to +30°C Ambient: -10°C to +35°C
Storage		Store in shaded dry conditions between +10°C and +30°C. Store canisters upright. The product is contained in a pressurised container - observe storage instructions and do not apply heat.
Shelf Life		15 months when stored as recommended in original unopened containers.

Necessary Tools

- illbruck foam gun, cutting knife, tape for masking of adjacent areas. AA290 PU Foam Cleaner to clear gun after use. Unstable areas may need to be clamped or secured during curing.

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Preparation

- Always carry out a test to confirm compatibility prior to use.
- Protect floor coverings with paper or a plastic film.
- The surfaces must be dry, solid, stable and capable of carrying the load of the panels to be installed.
- Remove all loose particles, dust and grease.
- A speedier cure can be attained by moistening the substrates if needed.



FM310

Pro Foam



Usage / Purpose

FM310 is suitable for general gap filling, bonding and insulation applications. These include the perimeter sealing and fixing of windows and doors, sealing of service penetrations and sealing around insulation panels.

Key Benefits

- Ideal for filling, sealing and insulation of joints and gaps in a variety of building and construction applications
- Low post expansion improves accuracy of delivery, reduces foam wastage and minimises cutting time
- Forms a strong bond to concrete, brickwork, stone, plaster, wood, fibre concrete, metal, PVC and polystyrene
- Rapid curing formulation: Foam is tack free within 10 minutes, and can be cut or trimmed within 45 minutes

Application

- Shake the canister vigorously at least 20 times. Remove the protective cap and screw canister onto the illbruck PU foam gun.
- For use with the AA210 nozzle, fix the nozzle on the valve and turn by 90 degrees before use. When using, the canister should be kept upside down. Foam volume is regulated by using the adjusting screw and gun's trigger.
- Joints should be underfilled to allow for post expansion of the foam. Fill to approximately 80% of joint depth for optimum results.
- For best results always work with the canister in a vertical position and keep the valve pointed downwards.
- On horizontal surfaces always work away from the exuding bead and work upwards on all vertical surfaces.
- When filling deep joints apply in layers, waiting until each layer has skinned and partially cured before applying the next.
- Applying a light misting of clean water between each layer before subsequent application will assist adhesion and cure speed.

Cleaning

Clean the gun by removing the foam canister and replacing with a can of AA290 PU Foam Cleaner. Remove excess foam immediately with AA290 PU Foam Cleaner or acetone. Ensure any substrate requiring cleaning is solvent resistant before proceeding. Cured foam can only be removed mechanically.

Please Note

FM310 is not UV resistant and should be protected from sunlight with a suitable opaque sealant, filler or paint. As with all PU foams, it does not bond to polythene, Teflon®, siliconised or wax-like surfaces.

Health & Safety Precautions

Safety data sheet must be read and understood before use. Extremely flammable- keep away from open flames and other ignition sources.



Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in

accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



Tremco CPG UK Limited
Coupland Road
Hindley Green, Wigan WN2 4HT
United Kingdom
T: +44 1942 251400
F: +44 1942 251410

info.uk@cpg-europe.com
www.cpg-europe.com